

# Datasheet

## RT479

### Prima Cortina waterstruck



Articlenr. 5 479 00 00

#### DETAILS FROM DOP

Brick type / Category	U / 1			
Intended use	Bricks for use in unprotected masonry			
Geometry	G1	In accordance with EN1996-1-1 holepercentage under 25		
Dimensions, [mm]	DK-NF	Length 228	Width 108	Height 54
Tolerance, [mm]	T2	Length $\pm 4$	Width $\pm 3$	Height $\pm 2$
Range, [mm]	Rm	Length 8	Width 6	Height 4
Gross density	1800	kg / m <sup>3</sup>		
Tolerance	D1	$\pm 10\%$		
Compressive strength, average, min	30	N/mm <sup>2</sup>		
Compressive strength, normalized, min	22	N/mm <sup>2</sup>		
Water absorption, maximum	11,5	Weight%		
Durability against freeze/thaw	F2	Freeze/thaw resistant		
Active soluble salts content (Category)	S2			
Fire resistance	A1	contains < 1,0% organic material		

#### SUPPLEMENTAL INFORMATION

Initial rate of absorption, average value $\pm$ tolerance	1,4 $\pm$ 0,4	kg/m <sup>2</sup>
Exposure class	MX3.2, MX4	
Bond strength	0,15	N/mm <sup>2</sup> , table value, EN 998-2, annex C
Bricks per m <sup>2</sup> with a 12mm mortar joint	63	pcs / m <sup>2</sup>
Palletising	80	pcs
Cleaning	Acid-cleaning is not allowed. See instructions for cleaning of masonry at <a href="http://randerstegl.com">randerstegl.com</a>	
Mortar selection	The type of mortar is chosen on the basis of characteristics of strength and durability in accordance with static impacts and exposureclass.	
Note	Brick is a natural material and variations can thus occur in terms of colour and structure. Therefore please see samples or reference buildings with the brick products in question.	



VINDØ TEGLVÆRK  
BLÅKILDEVEJ 19  
DK-9500 HOBRO

Revised 28/01/2021

Randers Tegl A/S  
Mineralvej 4  
DK-9220 Aalborg

Tlf: 98 12 28 44  
[info@randerstegl.dk](mailto:info@randerstegl.dk)  
[www.randerstegl.dk](http://www.randerstegl.dk)

**RANDERS Tegl**

SINCE 1911